



# TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453  
23825 15<sup>th</sup> Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815  
[DoctorTile@aol.com](mailto:DoctorTile@aol.com) [DoctorTile1@gmail.com](mailto:DoctorTile1@gmail.com) (805) 444-8453

TIA's Client: 20201228 BS

**Aquabella USA, LLC**  
**Mr. Brian L. Streadbeck**  
**450 South Alpine Highway**  
**Alpine, Utah 84004**

Telephone: (833) 985-2955  
[info@aquabellatile.com](mailto:info@aquabellatile.com)

**Tile: Italian Slate Series**

IS-634 - SAN MARINO 6X6	IS-234 - SAN MARINO 2X2	IS-634 SBN - SAN MARINO 6X6 S	IS-634 DECO - SAN MARINO 6X6 D
IS-635 - MILAN 6X6	IS-235 - MILAN 2X2	IS-635 SBN - MILAN 6X6 S	IS-635 DECO - MILAN 6X6 D
IS-637 - NAPLES 6X6	IS-237 - NAPLES 2X2	IS-637 SBN - NAPLES 6X6 S	IS-637 DECO - NAPLES 6X6 D
IS-638 - FIRENZE 6X6	IS-238 - FIRENZE 2X2	IS-638 SBN - FIRENZE 6X6 S	IS-638 DECO - FIRENZE 6X6 D

Conditions: New tiles were sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

## **TEST CONDUCTED:**

### **Resistance of Tile to Chemical Substances (ASTM C650)**

**Procedure:** This test method covers a procedure for determining whether, and to what degree, tiles are affected by prolonged exposure to chemical substances (10% Hydrochloric Acid & 10% Potassium Hydroxide). The temperature was controlled at 75±5 ° F (24±3 ° C) with an exposure time of 24 hours.

**Requirements:** ANSI A 137.1 (General). When tested as described in ASTM C 650, the Tile shall Not be affected.

The tile types and categories listed above yielded test values compliant with Industry's requirements.

Test Results: **Passed**

Sincerely,

Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021  
President/CEO of TILE INSTITUTE of AMERICA