

TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453
23825 15th Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815
DoctorTile@aol.com DoctorTile1@gmail.com (805) 444-8453

TIA's Client: 20201228 BS

Aquabella USA, LLC
Mr. Brian L. Streadbeck
450 South Alpine Highway
Alpine, Utah 84004

Telephone: (833) 985-2955
info@aquabellatile.com

Tile: Ocean Breeze Series

OB-350 - WINDSTREAM 3X3	OB-750 - WINDSTRM AKRON	OB-350-2 - WINDSTREAM 3X3 DBN	OB-550 - WINDSTREAM 1X2
OB-350-1 - WINDSTREAM 3X3 S.	OB-751 - SEASCAPE AKRON	OB-350-3 - WINDSTRM 1X3 QTR RD	OB-551 - SEASCAPE 1X2
OB-351 - SEASCAPE 3X3	OB-150 - WINDSTREAM 1X1	OB-350-4 - WINDSTRM 1X1 QTR RD	OB-801 - OCEAN BRZ BLEND 1X2
OB-351-1 - SEASCAPE 3X3 S.	OB-151 - SEASCAPE 1X1	OB-351-2 - SEASCAPE 3X3 DBN	OB-802 - LAGOON BLEND 1X
OB-353 - SURFSIDE 3X3	OB-153 - SURFSIDE 1X1	OB-351-3 - SEASCAPE 1X3 QTR RD	OB-900 - OCEAN BRZ BLEND 1X1
OB-354 - BREAKERS 3X3	OB-154 - BREAKERS 1X1	OB-351-4 - SEASCAPE 1X1 QTR RD	

Conditions: New tiles were sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

TEST CONDUCTED:

Resistance of Tile to Chemical Substances (ASTM C650)


Procedure: This test method covers a procedure for determining whether, and to what degree, tiles are affected by prolonged exposure to chemical substances (10% Hydrochloric Acid & 10% Potassium Hydroxide). The temperature was controlled at 75±5 ° F (24±3 ° C) with an exposure time of 24 hours.

Requirements: ANSI A 137.1 (General). When tested as described in ASTM C 650, the Tile shall Not be affected.

The tile types and categories listed above yielded test values compliant with Industry's requirements.

Test Results: **Passed**

Sincerely,

Handwritten signature of Gerald M. Halweg in black ink.

Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021
President/CEO of TILE INSTITUTE of AMERICA