



## TILE INSTITUTE of AMERICA

23825 15<sup>th</sup> Avenue SE #149, Bothell, WA 98021 & 240 Makee Road, Suite 9A, Honolulu, Hawaii 96815  
(805) 444-8453 [DoctorTile@aol.com](mailto:DoctorTile@aol.com) or [DoctorTile1@gmail.com](mailto:DoctorTile1@gmail.com)

TIA's Client: 20230928 FT  
October 20, 2023

AquaBella/Main Street Art, Inc.  
Mr. Brett Streadbeck  
Mr. Brian L. Streadbeck  
450 South Alpine Highway  
Alpine, Utah 84004

Telephone: (714) 264-8269  
[brett@aquabellatile.com](mailto:brett@aquabellatile.com), [brian@msagallery.com](mailto:brian@msagallery.com)

Tile: **PARADISE Series (PS-2365 HEAVEN) (PS-2366 EDEN)(PS-2367 DIVINE)** Factory  
"AB-8".

Nominal size: 2" x 3" x ¼". Tile made in China.

Conditions: New tiles were sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

### TEST CONDUCTED:

#### RESISTANCE TO FREEZE-THAW CYCLING (ASTM C 1026)

Standard Test Method for Measuring the Resistance of Tile to Freeze-Thaw Cycling.

Ten Specimens were placed into the freezing chamber to 0°F (-18°C) within a period of 6-8 hours and placed into water that was at a temperature from 50° to 60°F (10° to 16°C) for ≥30 minutes.

Requirements:

After 15 Cycles

The units are to show no evidence of Failure to Body or Surfaces.

No evidence of Disintegration.

Damage to the specimen is reported with the abbreviation as follows:

Cz = crazing, Ch = Chipping, Sp = spalling, Bc = body checks, Cr = cracks.

Results: All units described above have PASSED.

Sincerely,

Gerald M. Halweg, CTC, CSI, TTA.  
President/CEO of TILE INSTITUTE of AMERICA