



TILE INSTITUTE of AMERICA

TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453
23825 15th Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815
DoctorTile@aol.com DoctorTile1@gmail.com (805) 444-8453

TIA's Client: 20201228 RCS

**Aquabella USA, LLC Mr.
Brian L. Streadbeck 450 South
Alpine Highway Alpine, Utah
84004**

Title: North Seas Series

Telephone: (714) 264-8269 Facsimile: (714) 685-0465
brett@aquabellatile.com, brian@msagallery.com

NS-113 Caspian, NS-114 Norwegian, NS-115 Irish, NS-119 Adriatic, NS-120 Denmark, NS-1225 Arctic, NS-1219 Adriatic, NS-1220 Denmark, NS-1215 Irish, NS-1217 Baltic, NS-1216 Celtic, NS-1214 Norwegian, NS-1213 Caspian, NS-1212 Iceland, NS-1211 Greenland, NS-1210 Polar, NS-110 Polar, NS-111 Greenland, NS-112 Iceland.

Conditions: New tiles were sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

TEST CONDUCTED:

Resistance of Tile to Chemical Substances (ASTM C650)

Procedure: This test method covers a procedure for determining whether, and to what degree, tiles are affected by prolonged exposure to chemical substances (10% Hydrochloric Acid & 10% Potassium Hydroxide). The temperature was controlled at 75±5 ° F (24±3 ° C) with an exposure time of 24 hours.

Requirements: ANSI A 137.1 (General). When tested as described in ASTM C 650, the Tile shall Not be affected.

The tile types and categories listed above yielded test values compliant with Industry's requirements.

Test Results: **Passed**

Sincerely,

Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021
President/CEO of TILE INSTITUTE of AMERICA